

Central Lancashire Online Knowledge (CLoK)

Title	Experimental determination of the Fermi surface of Sr3Ir4Sn13
Туре	Article
URL	https://clok.uclan.ac.uk/14809/
DOI	https://doi.org/10.1103/PhysRevB.93.235121
Date	2016
Citation	Chen, X, Goh, SK, Tompsett, DA, Yu, WC, Klintberg, L, Friedemann, S, Tan, H, Yang, J, Chen, B et al (2016) Experimental determination of the Fermi surface of Sr3Ir4Sn13. Physical Review B (PRB), 93 (235121). pp. 1-5. ISSN 2469-9950
Creators	Chen, X, Goh, SK, Tompsett, DA, Yu, WC, Klintberg, L, Friedemann, S, Tan, H, Yang, J, Chen, B, Imai, M, Yoshimura, K, Gamza, M, Grosche, FM and Sutherland, ML

It is advisable to refer to the publisher's version if you intend to cite from the work. https://doi.org/10.1103/PhysRevB.93.235121

For information about Research at UCLan please go to http://www.uclan.ac.uk/research/

All outputs in CLoK are protected by Intellectual Property Rights law, including Copyright law. Copyright, IPR and Moral Rights for the works on this site are retained by the individual authors and/or other copyright owners. Terms and conditions for use of this material are defined in the <u>http://clok.uclan.ac.uk/policies/</u>

Supplemental Material for "Experimental Determination of the Fermi Surface of $Sr_3Ir_4Sn_{13}$ "

Xiaoye Chen,¹ Swee K. Goh,^{1,2} David A. Tompsett,³ Wing Chi Yu,² Lina Klintberg,¹

Sven Friedemann,^{1,4} Hong'En Tan,¹ Jinhu Yang,⁵ Bin Chen,⁵ M. Imai,⁵ Kazuyoshi

Yoshimura,⁵ Monika B. Gamza,⁶ F. Malte Grosche,¹ and Michael L. Sutherland¹

 $^1 Cavendish \ Laboratory, \ University \ of \ Cambridge,$

J. J. Thomson Avenue, Cambridge CB3 0HE, UK

²Department of Physics, The Chinese University of Hong Kong, Shatin, New Territories, Hong Kong, China

³Department of Chemistry, University of Bath, Bath BA2 7AY, UK

⁴HH Wills Laboratory, University of Bristol, BS8 1TL Bristol, UK

⁵Department of Chemistry, Graduate School of Science, Kyoto University, Kyoto 606-8502, Japan

⁶Department of Physics, Royal Holloway, University of London, Egham, TW20 0EX, UK

(Dated: May 23, 2016)

In this Supplemental Material, we list the angular dependence of the major frequencies, which was obtained in our rotation study, in Table S1 for the interest of the reader.

Angle ϕ (degrees)	Frequencies (T)					
20	64	229	-	-	1501	
25	66	232	-	-	1482	
30	64	240	-	-	1412	
35	75	260	-	664	1403	
40	93	265	421	-	1401	
45	93	311	415	647	1353	
50	71	249	-	-	1397	
55	49	246	-	-	1423	

TABLE S1. Table of angular dependence of major frequencies. ϕ denotes the angle between the applied field and the *a*-axis, with an overall uncertainty in the orientation of the crystal of ~ 5°.